

Garden

OUTDOOR



Manufacturing process

Herstellungsverfahren
Procédé de fabrication
Proceso de fabricación

ISO 2424

Needle felt

Pile composition

Polmaterial
Composition des fibres
Composición de la fibra

-

65% PES 35% PP

Surface structure

Oberflächenstruktur
Aspect de surface
Estructura de la superficie

-

Dilour

Backing

Rücken
Dossier
Soporte

ISO 2424

Resine

Pile weight

Polgewicht
Poids des fibres
Peso de la fibra

ISO 8543

590 g/m²

Total weight

Gesamtgewicht
Poids total
Peso total

ISO 8543

700 g/m²

Pile height

Polhöhe
Hauteur du velours
Altura de la fibra

ISO 1765

4 mm

Total height

Gesamthöhe
Hauteur totale
Altura total

ISO 1765

5 mm

Roll length

Länge
Longueur
Longitud del rollo

-

30 m

Fire classification

Brandklassifizierung
Classement feu
Clasificación de fuego

EN13501-1

Cfl-s1

UV stability

1500 h

