

REWIND®



REWIND 900 FLAT

CONTRACT



Using
zero latex



Using
zero water



With just a fraction
of energy use



Resulting in
significantly
lower CO₂



A division of
Beaulieu International Group
BFS Europe NV
Groenedreef 15A, 9770 Kruisem
www.beaulieu-needlefelt.com

beaulieu
needle felt



Manufacturing process

Herstellungsverfahren
Procédé de fabrication
Proceso de fabricación

ISO 2424

Needle felt

Pile composition

Polmaterial
Composition des fibres
Composición de la fibra

-

100% PP

Surface structure

Oberflächenstruktur
Aspect de surface
Estructura de la superficie

-

Flat

Backing

Rücken
Dossier
Soporte

ISO 2424

None - latex free

Pile weight

Polgewicht
Poids des fibres
Peso de la fibra

ISO 8543

900 g/m²

Total weight

Gesamtgewicht
Poids total
Peso total

ISO 8543

900 g/m²

Pile height

Polhöhe
Hauteur du velours
Altura de la fibra

ISO 1765

0 mm

Total height

Gesamthöhe
Hauteur totale
Altura total

ISO 1765

5 mm

Roll length

Länge
Longueur
Longitud del rollo

-

30 m

Permanent anti-static

Permanent antistatisch
Antistatique permanent
Antiestático permanente

ISO 6356

≤ 2kV

Prodis GUT Certificate

Prodis GUT Zertifikat
Certificat Prodis GUT
Certificado Prodis GUT

-

53EF76C9

Fire classification

Brandklassifizierung
Classement feu
Clasificación de fuego

EN13501-1

Bfl-s1



DNF.RO.MAR.15a/3/01-04-2024
Update: 02-2026