

REWIND FLAT

REWIND EVENT



Using
zero latex



Using
zero water



With just a fraction
of energy use



Resulting in
significantly
lower CO₂



A division of
Beaulieu International Group
BFS Europe NV
Groenedreef 15A, 9770 Kruisem
www.beaulieu-needlefelt.com



Manufacturing process Herstellungsverfahren Procédé de fabrication Proceso de fabricación	ISO 2424	Needle felt
Pile composition Polmaterial Composition des fibres Composición de la fibra	-	100% PP
Surface structure Oberflächenstruktur Aspect de surface Estructura de la superficie	-	Flat
Backing Rücken Dossier Soporte	ISO 2424	None - latex free
Pile weight Polgewicht Poids des fibres Peso de la fibra	ISO 8543	230 g/m ²
Total weight Gesamtgewicht Poids total Peso total	ISO 8543	230 g/m ²
Pile height Polhöhe Hauteur du velours Altura de la fibra	ISO 1765	0 mm
Total height Gesamthöhe Hauteur totale Altura total	ISO 1765	2 mm
Roll length Länge Longueur Longitud del rollo	-	50 m
Permanent anti-static Permanent antistatisch Antistatique permanente Antiestático permanente	ISO 6356	≤ 2kV
Prodis GUT Certificate Prodis GUT Zertifikat Certificat Prodis GUT Certificado Prodis GUT	-	943358A6
Fire classification Brandklassifizierung Classement feu Clasificación de fuego	EN13501-1	Bfl-s1

